

CrownTech™ - Technical Bulletin No. 7

Temperature, Humidity and Dew Point Guidelines

CONTENT

- Introduction
- Enclosed Facilities with HVAC
- Outside Installations or No HVAC
- Effects of Temperature
 - Low Temperature Installations
 - High Temperature Installations
- Effects of Humidity
 - Absolute Humidity
 - Relative Humidity
- Effects of Dew Point
- Cleaning Methods
- Dos and Don'ts

INTRODUCTION

The ambient temperature, substrate temperature, humidity and dew point will affect the handling properties, initial cure rate and ultimate mechanical properties of the cure product under the best conditions. Under adverse conditions the ambient temperature, substrate temperature, relative humidity and dew point will cause problems.

ENCLOSED FACILITIES WITH HVAC

The US Occupational Safety and Health Administration recommends that indoor air temperatures be maintained between 68°F to 76°F (20°C to 24.4°C), with the relative humidity between 20% to 60%. For enclosed facilities, with properly working HVAC systems, they can maintain the temperature and relative humidity. However, newly enclosed facilities or retrofit facilities without a working HVAC system are not acclimatized, which can cause problems.

OUTSIDE INSTALLATIONS OR NO HVAC

Outside applications or facilities without a working HVAC system are affected by the prevailing environmental conditions. Cold temperatures delay cure time and increase viscosity; inversely, warmer temperatures accelerate cure time and decrease viscosity. For those installations the temperature swings can be tremendous, often exceeding 50°F (28°C) from early in the morning to late evening. Extremely low relative humidity level can affect moisture cured polyurethanes, and high relative humidity can affect the evaporation rates of the moisture in waterborne and can interfere with chemical reaction of polyurethanes.

EFFECTS OF TEMPERATURE

Epoxies, polyaspartics, polyurethanes, etc. are polymer chemicals that cure into semi-rigid to hard surfaces when employed within their design limitations. These polymer coating and surfacing products cure to an inert lightweight, corrosive, abrasion and microbial resistance, and they possess other mechanical qualities that make them valuable material for use in construction and concrete surface repair. While epoxy remains durable under most everyday conditions, degradation of its polymer matrix can occur due to high temperatures and extremely low temperatures.

For best results with material intended for “ambient temperature installations” (not the materials designed to be applied at elevated temperatures), condition and install the material between 68°F to 76°F (20°C to 24.4°C), with the relative humidity between 20% to 60%. In addition, this technical bulletin does not address “in-use” elevated or lower temperatures.

Low Temperature Installations

1. Freezing
2. Crystallization
3. Increase in viscosity
4. Excessive material demand (due to increase in viscosity)
5. Protracted cure times
6. Amine blush
7. Arrested cure

High Temperature Installations

1. Shortened working time
2. Possibility of the top skinning over (entrapping solvent)
3. Lowering of viscosity
4. Resin starvation on slopes
5. Lap Lines (failure to hold a wet edge)
6. Flash set (poor bond)
7. Crater (no back flow)
8. Blister for outgassing
9. Stress cracking
10. Rough or uneven texture
11. Run especially on vertical surface

HUMIDITY

Polyurethanes and waterborne epoxies are sensitive to moisture. Polyurethane and waterborne epoxies are capable of being applied up to a maximum of 75% RH and as long as they are placed and cured at 5 degrees below the dew point. When there is excess moisture in the air, moisture can form on the surface of the coating film that will reduce the clarity of the finish, and may cause pin holing and foaming.

Early water contact with an uncured resin will contaminate the surface causing a variety of surface defects. As the relative humidity (moisture vapor) in the air increases, the potential for condensing as liquid increases as the dew point is approached.

For Polyurethane coatings, this can manifest itself as a milky haze or streaks.

EFFECTS OF HUMIDITY

Humidity is defined as the amount of water vapor (gaseous phase of water) in the air. It is an indicator of the presence of dew, frost, fog, and precipitation. The maximum water vapor which can be held in air is affected by temperature and atmospheric pressure variation. The higher the temperature, the greater the amount of water vapor it can hold before reaching a saturation point.

ABSOLUTE HUMIDITY

Absolute humidity is the measurement of the water content in the air typically in units of grams per cubic meter. It is calculated by dividing the total mass of water vapor by the volume of the air. Given the same amount of water vapor in air, the absolute humidity does not change with temperature at a fixed volume. If the volume is not fixed, as in the atmosphere, absolute humidity changes in response to the volume changes caused by the temperature and pressure variation.

RELATIVE HUMIDITY

Relative humidity compares the current ratio of absolute humidity to the maximum humidity for a given temperature and expresses this value as a percentage. The higher the percentage, the higher the humidity. It is affected by both temperature and atmospheric pressure. As an example, the same amount of water vapor will be a higher relative humidity in cool air than in warmer air.

Relative humidity is a commonly used metric in weather reports and forecasts and is a good indicator of precipitation, dew, frost, fog, and apparent temperature. Apparent temperature is the temperature perceived by humans. In summer, the higher the relative humidity, the higher the apparent temperature. This is a result of a higher humidity reducing the rate at which sweat evaporates, which increases perceived temperature.

A relative humidity of 100% indicates that the air is saturated, given the current conditions, water vapor in the air cannot increase further in normal conditions. 100% relative humidity is also the point at which dew can begin to form.

EFFECTS OF DEW POINT

Dew point is the temperature at which a given volume of air, at a certain atmospheric pressure, is saturated with water vapor, causing condensation, which results in the formation of dew.

Dew is the condensed water that is seen on the surface of objects. Dew point varies depending on the amount of water vapor present in the air, with more humid air resulting in a higher dew point than dry air. The higher the relative humidity, the closer the dew point to the current air temperature, with 100% relative humidity meaning that dew point is equivalent to the current temperature. (Dew point below freezing (0°C or 32°F), the water vapor turns directly into frost rather than dew.)

As long as the air temperature remains above the Dew Point, the air is unsaturated; i.e. it is capable of holding additional water vapor. Crown Polymers has adopted a "safe zone" of 5°F (2°C) above the Dew Point.

DEW POINT CHART

Dew Point – The temperature at which moisture will condense on a surface. No polymer coating should be installed unless the temperature is a minimum of 5°F (2°C) above this point.

Example: If the air temperature is 70°F and the relative humidity is 65%, the Dew Point is 57°F. No coating should be placed unless the surface temperature is 62°F or above.

Relative Humidity	Ambient Air Temperature – Fahrenheit								
	40°F	50°F	60°F	70°F	80°F	90°F	100°F	110°F	120°F
	The Surface Temperature On Which Moisture Condensation Occurs								
90%	37°F	47°F	57°F	67°F	77°F	87°F	97°F	107°F	117°F
85%	36°F	45%	55°F	65°F	74°F	84°F	95°F	104°F	113°F
80%	34°F	44°F	54°F	63°F	72°F	82°F	93°F	102°F	110°F
75%	33°F	42°F	52°F	62°F	70°F	80°F	91°F	100°F	108°F
70%	31°F	40°F	50°F	60°F	68°F	78°F	88°F	96°F	105°F
65%	29°F	38°F	47°F	57°F	67°F	76°F	85°F	94°F	103°F
60%	27°F	36°F	45°F	55°F	63°F	73°F	83°F	92°F	101°F
55%	25°F	34°F	43°F	53°F	60°F	70°F	80°F	89°F	98°F
50%	23°F	31°F	40°F	50°F	57°F	67°F	77°F	86°F	94°F
45%	21°F	29°F	37°F	47°F	54°F	64°F	73°F	82°F	91°F
40%	18°F	26°F	35°F	43°F	51°F	61°F	69°F	78°F	87°F

DISCLAIMER

The Technical Bulletin is intended to provide the most current data available to assist the Contractor is making the best decisions. All technical bulletins, installation guidelines, recommendations, statements, specifications, and technical data contained herein are based on information and tests. The accuracy and completeness of such tests are not guaranteed and are not to be construed as a warranty, expressed or implied. It is the responsibility of the user to document information and tests to determine the intent of the product for ones' own use. The application, job conditions and user assume all risks and liability resulting from use of the product. We do not suggest or guarantee any hazards listed herein are the only ones, which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use the product. Recommendations or statements, whether in written or verbal, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Crown Polymers makes no claim that these tests or any other tests accurately represent all environments. Not responsible for any typographical errors.

LIMITED WARRANTY

Crown Polymers warrants its products to be free of manufacturing defects and meets all Crown Polymers current published physical properties. Crown Polymers' sole responsibility shall be to replace the portion of any product proved to be defective. There are no other warranties by Crown Polymers of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Crown Polymers shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Crown Polymers shall not be responsible for the use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee pertaining to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator will be issued. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Crown Polymers reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

