

# 7000 CrownPro™ Aliphatic Polyaspartic Polyurea Topcoat

## TECHNICAL DATA SHEET Product Number: 7000

Fast Curing, High Performance, UV Stable, Aliphatic Polyaspartic Polyurea - Clear or Pigmented

### DESCRIPTION

**7000 CrownPro topcoat** is a two-component abrasion, chemical, and stain-resistant, fast-curing aliphatic polyaspartic polyurea topcoat. It is available in clear gloss and can be pigmented with CrownPigment™ PigmentPacks™. It cures to an inert, tough, impact, abrasion, and chemical resistance finish coat. It is resistant to Skydrol and many other mild chemicals, and Excellent adhesion to Crown Polymers epoxy systems. It requires a primer, 8105 CrownSeal Acrylic Polyurethane Primer, and Concrete Sealer when it is applied to properly prepared concrete and cementitious overlays. 7000 CrownPro topcoat is used as an upgraded topcoat on Crown Polymers products and systems used in aircraft hangars, industrial kitchens, automotive showrooms, and shop floors, commercial laboratories, and research facilities, hospital and health care, wine and spirit processing, and other facilities subjected to heavy foot traffic, forklift traffic and chemical attack. It is available in two working times. It is VOC Compliant in all states and provinces in North America.

### TYPICAL USES

- Aircraft Hangar and Maintenance Floors
- Automotive Show Room and Repair Floors
- Commercial Bakery and Kitchen Floors
- Food and Beverage Floors
- Hospital and Health Care Facility Floors
- Laboratory and Research Floors
- Manufacturing and Warehouse Floors
- Pharmaceutical Floors
- Clearcoat over decorative systems

### BENEFITS

- Complies with USDA, FDA, Food Safety Modernization Act. **See Crown Polymers Technical Bulletin: 3 Food and Beverage Compliance.**
- Slip Resistance (ADA) **See Crown Polymers Technical Bulletin: 4 Coefficient of Friction.**
- LEED® and Green Seal® requirements. **See Crown Polymers Technical Bulletin: 5 LEED and Green Seal Information.**
- VOC and EPA Compliant all states and provinces in North America. Cures to an inert finish. **See Crown Polymers Technical Bulletin: 2 VOC Compliance.**
- Strong and Tough Floor.
- Excellent Chemical and Abrasion Resistance
- Designed for new floors and for resurfacing old floors

### LIMITATIONS

- This product is best suited for applications when the temperature is between 60°F to 90°F (16°C to 32°C). Do not apply when Relative Humidity exceeds 85%. **See Crown Polymers Technical Bulletin: 7 Temperature and Relative Humidity Limits.**

- Higher temperatures will result in shortened working time and drying time.
- Requires primer when applied directly to concrete and cementitious overlays. **See Crown Polymers Technical Bulletin: 20 Selecting a Primer.**

### COLORS

- Clear Gloss. Pigments available in standard colors by adding CrownPigment SB Polyurethane PigmentPacks Series 6600 available in 15 standard colors. **\*See Crown Polymers Standard Color Guide Acrylics, Epoxies, Polyaspartics, Polyurethanes (PigmentPack).**

### COVERAGE RATE PER GALLON

- Clear Gloss and Pigmented Top Coat: 134 to 200 sq. ft. (12.5 to 13.6 sq. m) WFT 8 – 12 mils (0.20 – 0.30 mm)

### CONCRETE

Concrete must be structurally sound and free of curing agents, coatings, sealers, densifiers, and other bond breakers.

#### New Concrete:

- Place concrete per ACI 302.2R Guide for Concrete Slabs that Receive Moisture-Sensitive Floor Materials.
- Water Cement Ratio 0.4 to 0.5, and an approximate 4,000 psi (28 MPa) strength level.
- Requiring a positive side moisture barrier in direct contact with the concrete meeting ASTM E1745 Standard Specification for Plastic Water Retarders Used in Contact with Soil or Granular Fill under Concrete Slabs.

- The moisture barrier needs to be placed per ASTM E1643 Standard Practice for Selection, Design, Installation of Water Vapor Retarders Used in Contact with Earth or Granular Fill Under Concrete Slabs, Class A 15 mils (0.38mm)

**Existing Concrete:**

If field tests or laboratory analysis reveals inferior concrete flooring slabs containing contaminants from previously applied unreacted silicate materials that will interfere with the bond, use 8201 CrownPrime WBC. **See Crown Polymers Technical Bulletin: 20 Selecting a Primer.**

- Contaminants include, but are not limited to organic hydrocarbon materials, calcium chlorides, and aluminum stearates.
- Concrete flooring slab can lose their structural strength over time, caused by conditions beyond the control of

- the flooring manufacturer or the installation contractor.
- If the concrete substrate deteriorates sufficiently, it will no longer support the bond of the remediation floor system.

Such conditions are detailed in ACI 201.2R “Guide to Durable Concrete” published by the American Concrete Institute. **See Crown Polymers Technical Bulletin: 1 Concrete Surface Preparation.**

Physical Properties at 77°F (25°C) (Unless stated otherwise)	
VOC (Volatile Organic Compounds), (VOC Calculated Per ASTM D3960)	0 gr./lt.
Standard Viscosity Clear, Mixed Epoxy and Hardener	900 – 1,200 cps
Pot Life, Standard Cure, 1 quart (0.95 liters) Mass, Pot Life is Reduced by Increases in Mass and Temperature*	10 – 15 Minutes
Mix Ratio, by Volume	1:1
Dry to Touch 60°F to 90°F (16°C to 32°F)	2 to 4 Hours
Recoat Time 60°F to 90°F (16°C to 32°F)	12 to 72 Hours
Vehicle Traffic (depending on surface temperature and relative humidity)	2 to 4 days
Light Traffic 60°F to 90°F (16°C to 32°F)	12 Hour Minimum
Full Cure 60°F to 90°F (16°C to 32°F)	4 to 14 Days
Shelf Life (shipped and stored) at 60°F to 100°F (16°C to 38°C)	1.0 Year

Mechanical Properties at 77°F (25°C)			
Surface Preparation ICRI 310.2R Concrete Surface Profile (CSP 2 and above) Depending on System to be Installed and Condition of Concrete.			
	40°F (4°C)	77°F (25°C)	90°F (32°C)
Compressive Strength, ASTM D695	1,100 psi	1,200 psi	1,400 psi
Adhesion to Concrete, ASTM D7234	245 psi	280 psi	290 psi
Tensile Strength, ASTM D638	1,000 psi		
Tensile Elongation, ASTM D638	80% - 100%		
Hardness (Shore D) ASTM D2240	35 - 40		
Water Absorption, ASTM D570 Resin & Hardener	0.6%		
Moisture Vapor Emission Rate, ASTM F1869*	3 lbs.		
Moisture Relative Humidity, ASTM F2170*	80% RH		

\*If moisture or relative humidity exceeds the limits consult the Crown Polymers representative and refer to **Crown Polymers Technical Bulletin: 6 Moisture Mitigation Negative Side Moisture Barrier**

**Note:** Although testing is critical, it is not a guarantee against future problems. This is especially true if there is not a positive side vapor barrier or it is not functioning properly and/or concrete has contamination from oils, chemical spills, densifiers, excessive salts or other bond breakers.

## CHEMICAL RESISTANCE DATA

See **Crown Polymers Technical Bulletin: 9 Chemical Resistance Guidelines and Chart.**

## CHECK CONCRETE MOISTURE

The concrete must be dry before application of this floor coating material. Concrete moisture tests are required, either ASTM F1869 (calcium chloride) or ASTM F2170 (in situ RH probe). **Refer to appropriate Technical Data Sheet limits and Crown Polymers Technical Bulletin: 6 Moisture Mitigation Negative Side Moisture Barrier.**

## CHECK TEMPERATURE & HUMIDITY

Floor and material temperature must be at or above the published Technical Data Sheet. Dew Point must be 5°F (3°F) or more below the surface temperature. Do not apply if humidity is at or above 85%. **See Crown Polymers Technical Bulletin: 7 Temperature and Relative Humidity Limits.**

## SURFACE PREPARATION

Surface preparation per: ICRI Guideline No. 310.2R Selecting and Specifying Concrete Surface Preparation for Sealers, Coatings, Polymer Overlays, and Concrete Repair. The pH of the concrete substrate should be at 9 or above. All bond-breaking material must be removed. **See Crown Polymers Technical Bulletin: 1 Concrete Surface Preparation.**

## APPLICATION EQUIPMENT

Depending on system applied: Variable low-speed drill (450 rpm) with Jiffy® type impeller mixing paddle, disposable 3" brush for cutting in, 3/8 inch nap non-shedding phenolic core roller, and rubber squeegee for spreading 8175 CrownPro Polyaspartic. Pour, squeegee, and back-roll are suggested because Dip-n-Roll can be challenging for inexperienced installers resulting in unattractive lap lines.

## MIXING

For ease of mixing and placement, the temperature of the "A" and "B" components should be between 70°F to 80°F (20°C to 26°C). Pre-mix the "A" and "B" components to ensure all raw material and pigments are dispersed uniformly. **See Crown Polymers Technical Bulletin: 10 Mixing Guidelines.**

## APPLICATION

pour all liquid material onto the properly prepared concrete substrate or next lift in ribbons and squeegee the material out evenly. Back-rolling and cross rolling of material. Check for desired wet film thickness with a WFT Gauge. If broadcasting aggregate, such as 60 mesh or 90 mesh, broadcast a sprinkle (not full broadcast) into the wet material. Place all steps per Crown Polymer Installation Guidelines.

## SKID-RESISTANCE

Skid-Resistance – Field (in situ) Wet Dynamic Coefficient of Friction (DCOF), ANSI A326.3. **See Crown Polymers Technical Bulletin: 12 Coefficient of Friction.**

## SHIPPING and STORAGE

Ship and store material between 40°F to 90°F (4°C to 32°C). Store in a dry environment and out of direct sunlight.

## SHELF LIFE

Shelf life is 1 year from the date of manufacture, provided the containers are unopened.

## CLEAN-UP

Clean-up mixing station, tools, and equipment as required. Use acetone, a VOC exempt solvent, for cleaning up. Observe all legal, and health, and safety precautions when handling or storing solvents and materials, particularly in confined spaces. Make sure the working areas are well ventilated at all times during placement and curing time.

## DISPOSAL

Dispose of empty packaging and other waste per federal, state, province, and local regulations.

## MAINTENANCE

Inspect the installed floor by spot cleaning and spot repairing the damaged or cracked areas. To prolong the life of the flooring system, a daily maintenance program is highly recommended to ensure the floor is safe for its intended purposes. **See Crown Polymers Technical Bulletin: 8 Care and Maintenance.**

## TECHNICAL SUPPORT

For questions, contact a Crown Polymers Representative. Additional Support Documents are available from Crown Polymers, including brochures, application guidelines, videos and more. Visit [Crownpolymers.com](http://Crownpolymers.com) or contact Crown for additional resources.

---


#### **DISCLAIMER**

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests. The accuracy and completeness of such tests are not guaranteed and are not to be construed as a warranty, expressed or implied. It is the responsibility of the user to document information and tests to determine the intent of the product for ones' own use. The application, job conditions and user assumes all risks and liability resulting from use of the product. We do not suggest or guarantee any hazards listed herein are the only ones, which may exist. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use the product. Recommendations or statements, whether in written or verbal, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by a corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Crown Polymers makes no claim that these tests or any other tests accurately represent all environments. Not responsible for any typographical errors.

#### **LIMITED WARRANTY**

Crown Polymers warrants its products to be free of manufacturing defects and meets all Crown Polymers current published physical properties. Crown Polymers' sole responsibility shall be to replace the portion of any product proved to be defective. There are no other warranties by Crown Polymers of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Crown Polymers shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. Crown Polymers shall not be responsible for the use of this product in a manner to infringe on any patent held by others. In addition, no warranty or guarantee pertaining to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by the applicator will be issued. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of the substrate or structural defects are also excluded from the limited warranty. Crown Polymers reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator.

---



Crown Polymers Corp. • Tel: 847.659.0300 • Fax: 847.659.0310  
info@crownpolymers.com • www.crownpolymers.com  
© 2022 Crown Polymers Corp. All rights reserved

CP 7000 CrownPro Aliphatic Polyaspartic Polyurea High Solids TDS 20220719DM

Page: 4 of 4