

## PHYSICAL PROPERTIES

<b>SOLIDS CONTENT</b>	.....	100%
<b>VOLUMETRIC MIX RATIO</b>	.....	1A:1B
<b>COVERAGE RATE</b>	.....	Primer: 200 ft <sup>2</sup> /gal 8 Mills Build Coat: 100 ft <sup>2</sup> /gal 16 Mills Topcoat: 160 ft <sup>2</sup> /gal 10 Mills
<b>APPLICATION TEMP</b>	.....	50°- 90°F
<b>POTLIFE</b> 1 Gal mass @ 75°F	.....	20 Min
<b>DRY TIME</b> @ 75°F	.....	4-6 Hours
<b>RECOAT WINDOW</b>	.....	8-24 Hours
<b>FULL CURE</b>	.....	7 Days
<b>PACKAGING</b>	.....	2 Gal Kit 10 Gal Kit

## MECHANICAL PROPERTIES

<b>COMPRESSIVE STRENGTH</b> ASTM D695	.....	12,000 p.s.i
<b>TENSILE STRENGTH</b> ASTM D638	.....	4,500 p.s.i
<b>ELONGATION</b> ASTM D638	.....	2%
<b>ADHESION TO CONCRETE</b> ASTM D7234	.....	>400 p.s.i
<b>WATER ABSORPTION</b> ASTM D570	.....	0.15%
<b>SHORE D HARDNESS</b> ASTM D2240	.....	80-85
<b>ABRASION RESISTANCE</b> ASTM D4060	.....	0.026 gr

## CHEMICAL RESISTANCE

Refer to CrownTech Chemical Resistance Guideline Technical Bulletin No. 9

## PRODUCT DESCRIPTION

7500 CrownPro AcidShield is a multifunctional phenol novolac resin that is extremely chemical resistant. 7500 CrownPro AcidShield is a moderate viscosity thick film novolac lining designed to cure at ambient temperatures to provide superior corrosion protection for surfaces in severe chemical and physical environments. It can be applied directly over 8303 CrownShield™ MVB (moisture mitigation primer). It is VOC Compliant in all states and provinces in North America.


## TYPICAL USES

- Crude Oil Storage Tanks
- Mining & Milling Industries
- Secondary Containment Areas
- Water & Waste Water Treatment Plants
- Food Processing Facilities
- Petrochemical Plants
- Semi-Conductor Manufacturing & Etching
- Power Generating Plants

## BENEFITS

- Complies with USDA, FDA, FSMA. See Crown Polymers Technical Bulletin: 3 Food and Beverage Compliance.
- LEED requirements. See Crown Polymers Technical Bulletin: 5 LEED information
- Cures to an inert finish. See Crown Polymers Technical Bulletin: 2 VOC Compliance

## COLORS



## LIMITATIONS

- Higher temperatures will result in shortened working times and faster drying time.
- Color may vary due to batch-to-batch variation, always “box” different batches to avoid it.
- Use 8303 CrownShield™ Moisture Barrier when MVT exceeds 3 lbs. or 80% RH
- May amber with UV Exposure
- Will not bridge cracking
- Do not thin

## SHELF LIFE

1 Year from Date of Manufacture provided unopened

## STORAGE

Store in a dry environment at room temperature and out of direct sunlight.

## APPLICATION EQUIPMENT

Personal Protective Equipment  
Jiffy Mixing Paddle  
Drill  
18" x 3/8" Nap Shedless Roller Cover  
8-12 or 15-20 Mil Notched Squeegee  
4" Chip Brush  
Spike Shoes

## SURFACE DIAGNOSTICS

Concrete must be structurally sound and free of all contaminants and bond breakers. Test concrete compressive strength using a Schmidt or Rebound Hammer to ensure substrate has compressive strength of 3500 psi or higher.

Perform a pH test using concrete pH test strips or meter to ensure substrate pH is between 9-12.

Perform Moisture Test using either Calcium Chloride per ASTM F1869 or In-Situ Relative Humidity Probe per ASTM F2170 to ensure substrate has Moisture Vapor Emission Rate of 3 psi or less and Relative Humidity of 80% or less. See CrownTech Bulletin 6: Moisture Mitigation Negative Side Moisture Barrier

If Moisture Vapor Emission Rate is above 3 psi. but below 25 psi. and relative humidity is above 80% but below 99% then apply 8303 Moisture Barrier Primer first at 16 mils with a coverage rate of 100 Ft<sup>2</sup> / Gal.

## SURFACE PREPARATION

Use Mohs scratch test to determine concrete hardness for proper diamond bond selection.

Concrete should be mechanically profiled and prepared to produce a Concrete Surface Profile (CSP) level between #2 & #4 per ICRI Guideline no. 310.2R. See CrownTech Bulletin 1: Concrete Surface Preparation.

All perimeter areas of coating termination shall be masked for protection. Saw cut and key-in all termination points.

## SURFACE REPAIR

All depressions, divots and cracks should be profiled and free of dust and contaminants. Repair surface imperfections to reduce the ability to see the defect through the coating.

Honor all dynamic (moving) joints, static joints may be filled, use dynamic joints as initiation and termination points during application process where needed.

## TEMPERATURE EVALUATION

Ambient and substrate temps should be above 50°F and a minimum of 5°F above Dew Point.

Product temps should be between 70-80°F.

Relative Humidity should not exceed 80%. See CrownTech Bulletin 7: Temperature & Relative Humidity

**ALL SOURCES OF IGNITION SHOULD BE TURNED OFF AND ENVIRONMENT SHOULD HAVE PROPER AND ADEQUATE VENTILATION DURING APPLICATION AND CURING PROCESS**

**MIXING AREA SHOULD BE PLACED ON OR IN CLOSE PROXIMITY TO PROJECT. AREA SHOULD BE SECURELY COVERED WITH PLASTIC, CARDBOARD OR TARP. STAGE MATERIALS, TOOLS AND CLEANING SUPPLIES IN MIXING AREA PRIOR TO APPLICATION PROCESS.**

**DO NOT MIX MORE MATERIAL THAN CAN BE APPLIED IN 20 MINUTES**

## MIXING

**1** Pre-Mix A-Component in its respective container using Jiffy mixer and drill at slow speeds for 1 minute until pigment is uniform.

**IF USING MULTIPLE BATCHES, IT IS BEST TO BOX ALL A-COMPONENTS TOGETHER THEN SEPARATE BACK INTO INDIVIDUAL CONTAINERS TO ENSURE EVEN PIGMENTATION.**

**2** Pre-Mix B-Component in its respective container using clean Jiffy mixer and drill at slow speeds for 30 seconds or until thoroughly homogeneous.

**3** Transfer A-component and B-component at a mix rate of 1A:1B by volume into a clean 5-gal bucket and mix for 2-3 minutes being sure to scrape sides of the bucket with a stir stick ensuring both components are thoroughly blended

## COVERAGE RATE

**Primer: 200 Ft<sup>2</sup> / Gal @ 8 Mils**  
**Build Coat: 100 Ft<sup>2</sup> / Gal @ 16 Mils**  
**Topcoat: 160 Ft<sup>2</sup> / Gal @ 10 Mils**

**COVERAGE RATE MAY VARY DEPENDING ON SUBSTRATE CONDITION AND POROSITY**

## WORKING TIME

**15-30 Minutes @ 75°F**

**WARMER AMBIENT, PRODUCT AND SURFACE TEMPERATURES WILL SHORTEN POTLIFE AND WORKING TIME.**

## APPLICATION PROCEDURE

**1** Cut-in edges using a 4" chip brush. Do not allow wet edges to stand more than 10 minutes ahead of application of main body of floor.

**EPOXY SETS FASTER IN MASS, MIXED MATERIAL SHOULD NOT REMAIN IN BUCKET**

**2** Pour a band of mixed material across the surface roughly 6-8" wide. Use 8-12 or 15-20 mil notched squeegee to gauge material across surface depending on application

- Maintain wet edge
- Always pour next mixed batch onto wet edge
- Do not apply heavier than recommended coverage rates

**3** Back roll the surface with 18" x 3/8" nap roller by walking into the wet material wearing spike shoes and roll the surface wall to wall with overlap perpendicular to your first pass

- Do not overwork material

**✓** Allow coating to dry 4-6 Hrs @ 75°F  
Do not force dry.  
Recoat: 4-24 Hrs  
Light Traffic: 24 Hours  
Heavy Traffic: 48 Hours  
Equipment Traffic: 72 Hours

## SLIP RESISTANCE

Skid-Resistance – Field (in situ) Wet Dynamic Coefficient of Friction (DCOF), ANSI A326.3. See Crown Polymers Technical Bulletin: 4 Coefficient of Friction.

## CLEAN-UP

Clean-up mixing station, tools, and equipment as required. Use acetone, a VOC exempt solvent, for cleaning up. Observe all legal, and health, and safety precautions when handling or storing solvents and materials, particularly in confined spaces. Make sure the working areas are well ventilated at all times during placement and curing time.

## DISPOSAL

Dispose of empty packaging and other waste in accordance with federal, state, provinces and local regulations.

## MAINTENANCE

Inspect the installed floor by spot cleaning and spot repairing the damaged or cracked areas. To prolong life of the flooring system, a daily maintenance program is highly recommended to ensure the floor is safe for its intended purposes. See Crown Polymers Technical Bulletin: 8 Care and Maintenance.

## TECHNICAL SUPPORT

For questions, contact a Crown Polymers Representative. Additional Support Documents are available from Crown Polymers, including brochures, application guidelines, videos and more. Visit [Crownpolymers.com](http://Crownpolymers.com) or contact Crown for additional resources

## DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any product limitations are the only ones which may exist. Neither Seller nor Manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the products. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the Manufacturer, unless in writing and signed by an authorized corporate officer of Manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Manufacturer makes no claim that these tests or any other tests accurately represent all environments. Manufacturer is not responsible for typographical errors.



**SCAN QR CODE FOR FULL DISCLAIMER AND LIMITED WARRANTY INFORMATION**

## REFER TO SAFETY DATA SHEETS (SDS)

### FOR SAFETY PRECAUTIONS.

**SAFETY PRECAUTIONS MUST BE FOLLOWED DURING STORAGE, HANDLING AND USE.**

## PERSONAL PROTECTIVE EQUIPMENT (PPE)

**SHALL BE WORN AT ALL TIMES INCLUDING BUT NOT LIMITED TO LONG SLEEVE SHIRTS OR DISPOSABLE ARM SLEEVES, SAFETY GLASSES, DISPOSABLE NITRILE GLOVES, AND PROPERLY FITTED NIOSH RESPIRATORS**