

## PHYSICAL PROPERTIES

<b>VOC</b>	.....	<140 g/L
<b>SOLIDS CONTENT</b>	.....	85%
<b>VOLUMETRIC MIX RATIO</b>	.....	2A:1B
<b>COVERAGE RATE</b>	.....	150 ft <sup>2</sup> /gal 10.7 Mills
<b>POTLIFE</b> 1 Gal mass @ 75°F	.....	20-25 Min
<b>DRY TIME</b> @ 75°F	.....	6-8 Hours
<b>RECOAT WINDOW</b>	.....	4-12 Hours
<b>FULL CURE</b>	.....	7 Days
<b>PACKAGING</b>	.....	3 Gal Kit 15 Gal Kit

## MECHANICAL PROPERTIES

<b>GLOSS INDEX 60°</b> ASTM D3363	.....	90-95
<b>TENSILE STRENGTH</b> ASTM D412	.....	4,000 psi
<b>ELONGATION</b> ASTM D412	.....	40%

## CHEMICAL RESISTANCE

Refer to CrownTech Chemical Resistance Guideline Technical Bulletin No. 9

## PRODUCT DESCRIPTION

8020 CrownPro is a two-component, abrasion, chemical, and stain-resistant polyaspartic topcoat. It is available in clear gloss. It cures to an inert, tough, impact, abrasion, and chemical resistance finish coat. It is resistant to Skydrol, betadine, and conventional hot-tire staining. Excellent adhesion to Crown Polymers epoxy flooring systems providing an added protective layer to prolong the longevity of the flooring system. 8020 CrownPro is used in facilities subjected to heavy foot traffic, forklift traffic and chemical attack. It is VOC Compliant in all states and provinces that do not follow SCAQMD VOC Limits.

## TYPICAL USES

• Aircraft Hangars & Maintenance Floors	• Commercial Bakeries and Kitchens	• Laboratories and Research Floors	• School & Universities
• Automotive Show Room and Repair Areas	• Hospital and Health Care Facility Floors	• Manufacturing and Warehouse Floors	• Pharmaceutical Floors

## BENEFITS

- Resists a very wide range of organic and inorganic acids, alkalis, amines, salts and solvents
- Durable, impermeable and seamless
- Excellent chemical resistance
- Superior mechanical resistance
- Low maintenance
- Cures quickly, fast turnaround
- Excellent UV resistance
- Superior aesthetic finish

## COLORS



Clear Gloss

## LIMITATIONS

- Higher temp/humidity will result in shortened working times and faster drying time.
- Do not dilute with solvents
- Use 8303 CrownShield™ Moisture Barrier when MVT exceeds 3 lbs. or 80% RH
- Do not apply heavier than recommended coverage rate
- Do not apply direct to concrete

## SHELF LIFE

1 Year from Date of Manufacture provided unopened

## STORAGE

Store in a dry environment at room temperature and out of direct sunlight.

## APPLICATION EQUIPMENT

Personal Protective Equipment  
Jiffy Mixing Paddle  
Drill  
18"x 3/8" Nap Shedless Roller Cover  
8-12 Mil Notched Squeegee  
4" Chip Brush  
Spike Shoes

## SURFACE DIAGNOSTICS

Concrete must be structurally sound and free of all contaminants and bond breakers. Test concrete compressive strength using a Schmidt or Rebound Hammer to ensure substrate has compressive strength of 3500 psi or higher.  
Perform a pH test using concrete pH test strips or meter to ensure substrate pH is between 9-12.  
Perform Moisture Test using either Calcium Chloride per ASTM F1869 or In-Situ Relative Humidity Probe per ASTM F2170 to ensure substrate has Moisture Vapor Emission Rate of 3 lbs or less and Relative Humidity of 80% or less. See CrownTech Bulletin 6: Moisture Mitigation Negative Side Moisture Barrier

If Moisture Vapor Emission Rate is above 3 lbs but below 25 lbs and relative humidity is above 80% but below 99% then apply 8303 Moisture Barrier Primer first at 16 mils with a coverage rate of 100 Ft<sup>2</sup>/ Gal.

## SURFACE PREPARATION

Use Mohs scratch test to determine concrete hardness for proper diamond bond selection.  
Concrete should be mechanically profiled and prepared to produce a Concrete Surface Profile (CSP) level between #2 & #4 per ICRI Guideline no. 310.2R. See CrownTech Bulletin 1: Concrete Surface Preparation.  
All perimeter areas of coating termination shall be masked for protection. Saw cut and key-in all termination points.

## SURFACE REPAIR

All depressions, divots and cracks should be profiled and free of dust and contaminants. Repair surface imperfections to reduce the ability to see the defect through the coating.  
Honor all dynamic (moving) joints, static joints may be filled, use dynamic joints as initiation and termination points during application process where needed.

## CLIMATE EVALUATION

Ambient and substrate temps should be above 50°F and a minimum of 5°F above Dew Point.  
Product temps should be between 70-80°F.  
Atmospheric Relative Humidity should not exceed 80%. See CrownTech Bulletin 7: Temperature & Relative Humidity

### REFER TO SAFETY DATA SHEETS (SDS) FOR SAFETY PRECAUTIONS.

SAFETY PRECAUTIONS MUST BE FOLLOWED  
DURING STORAGE, HANDLING AND USE.

### PERSONAL PROTECTIVE EQUIPMENT (PPE)

SHALL BE WORN AT ALL TIMES INCLUDING  
BUT NOT LIMITED TO LONG SLEEVE SHIRTS OR  
DISPOSABLE ARM SLEEVES, SAFETY GLASSES,  
DISPOSABLE NITRILE GLOVES, AND PROPERLY  
FITTED NIOSH RESPIRATORS

ALL SOURCES OF IGNITION SHOULD  
BE TURNED OFF AND ENVIRONMENT  
SHOULD HAVE PROPER AND ADEQUATE  
VENTILATION DURING APPLICATION AND  
CURING PROCESS

MIXING AREA SHOULD BE PLACED ON OR IN  
CLOSE PROXIMITY TO PROJECT. AREA SHOULD  
BE SECURELY COVERED WITH PLASTIC,  
CARDBOARD OR TARP. STAGE MATERIALS,  
TOOLS AND CLEANING SUPPLIES IN MIXING  
AREA PRIOR TO APPLICATION PROCESS.

DO NOT MIX MORE MATERIAL THAN CAN BE  
APPLIED IN 20 MINUTES

## MIXING PROCEDURE

1

Pre-Mix A-Component in its respective container using Jiffy mixer and drill at low RPMs for 30 seconds to ensure components are fully suspended.

IF USING CROWN POLYMERS 6600 SERIES PIGMENT PACKS, IT IS BEST TO BOX ALL A-COMPONENTS TOGETHER THEN SEPARATE BACK INTO INDIVIDUAL CONTAINERS TO ENSURE EVEN PIGMENTATION.

2

Pre-Mix B-Component in its respective container using clean Jiffy mixer and drill at slow speeds for 30 seconds or until thoroughly homogeneous.

3

Transfer A-component and B-component at a mix rate of 2A:1B by volume into a clean 5-gal bucket and mix for 2-3 minutes at low RPMs being sure to scrape sides of the bucket with a stir stick ensuring both components are thoroughly blended

## COVERAGE RATE

150 Ft<sup>2</sup> / Gal @ 10.7 mils

COVERAGE RATE MAY VARY DEPENDING ON SUBSTRATE  
CONDITION AND APPLICATION

## WORKING TIME

15-20 Minutes @ 75°F & 50% RH

WARMER AMBIENT, PRODUCT AND SURFACE TEMPERATURES  
AS WELL AS HIGHER RELATIVE HUMIDITY WILL SHORTEN  
POTLIFE AND WORKING TIME.

## APPLICATION PROCEDURE

1

Cut-in edges using a 4" chip brush. Do not allow wet edges to stand more than 10 minutes ahead of application of main body of floor.

POLYASPARTIC SETS SLOWER IN MASS, MIXED MATERIAL  
SHOULD BE POURED AS NEEDED

2

Pour a band of mixed material across the surface roughly 6-8" wide. Use 8-12 mil notched squeegee to gauge material across surface

- Maintain wet edge
- Always pour next mixed batch onto wet edge
- Do not apply heavier than recommended coverage rates

3

Back roll the surface with 18" x 3/8" nap roller by walking into the wet material wearing spike shoes and roll the surface wall to wall with overlap perpendicular to your first pass

- Do not overwork material

✓

Allow coating to dry 6-8 Hrs @ 75°F  
Do not force dry.  
Recoat: 2-12 Hours  
Light Traffic: 24 Hours  
Heavy Traffic: 48 Hours  
Equipment Traffic: 72 Hours

## SLIP RESISTANCE

Skid-Resistance – Field (in situ) Wet Dynamic Coefficient of Friction (DCOF), ANSI A326.3. See Crown Polymers Technical Bulletin: 4 Coefficient of Friction.

## CLEAN-UP

Clean-up mixing station, tools, and equipment as required. Use acetone, a VOC exempt solvent, for cleaning up. Observe all legal, and health, and safety precautions when handling or storing solvents and materials, particularly in confined spaces. Make sure the working areas are well ventilated at all times during placement and curing time.

## DISPOSAL

Dispose of empty packaging and other waste in accordance with federal, state, provinces and local regulations.

## MAINTENANCE

Inspect the installed floor by spot cleaning and spot repairing the damaged or cracked areas. To prolong life of the flooring system, a daily maintenance program is highly recommended to ensure the floor is safe for its intended purposes. See Crown Polymers Technical Bulletin: 8 Care and Maintenance.

## TECHNICAL SUPPORT

For questions, contact a Crown Polymers Representative. Additional Support Documents are available from Crown Polymers, including brochures, application guidelines, videos and more. Visit [Crownpolymers.com](http://Crownpolymers.com) or contact Crown for additional resources

## DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any product limitations are the only ones which may exist. Neither Seller nor Manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the products. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the Manufacturer, unless in writing and signed by an authorized corporate officer of Manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Manufacturer makes no claim that these tests or any other tests accurately represent all environments. Manufacturer is not responsible for typographical errors.



SCAN QR CODE FOR FULL DISCLAIMER AND LIMITED  
WARRANTY INFORMATION