

## PHYSICAL PROPERTIES

<b>VOC</b>	.....	<100 g/L
<b>SOLIDS CONTENT</b>	.....	35-38%
<b>MIX RATIO</b>	.....	Single Component
<b>COVERAGE RATE</b>	.....	Sealer: 300 ft <sup>2</sup> /gal 5.3 Mils
<b>APPLICATION TEMP</b>	.....	50° - 90°F
<b>DRY TIME</b> @ 75°F	.....	30-60 Mins
<b>RECOAT WINDOW</b>	.....	1 Hour
<b>FULL CURE</b>	.....	7 Days
<b>PACKAGING</b>	.....	1 Gal Kit 5 Gal Kit

## MECHANICAL PROPERTIES

<b>ADHESION TO CONCRETE</b> ASTM D7234	.....	>300 p.s.i
<b>MOISTURE VAPOR EMISSION</b> ASTM F1869	.....	Breathable

## CHEMICAL RESISTANCE

Refer to CrownTech Chemical Resistance Guideline Technical Bulletin No. 9

## PRODUCT DESCRIPTION

8101 CrownSeal is a single component, waterborne, ultraviolet stable, high-performance, fast-drying acrylic emulsion. It is used as a vinyl chip as a clear grout coat, and it is used as a Concrete, Cementitious Overlays, Masonry and Porous Bricks and Pavers sealer. As a grout coat for CrownFlake vinyl chips it should be placed at 200 sq. ft. per gallon. As a sealer place of clean, sound, and durable Concrete, Cementitious Overlays, and Masonry at 300 to 350 sq. ft. per gallon. Porous Bricks and Porous Pavers the sealer demand will vary depending on their porosity. It is VOC Compliant in all states and provinces in North America.

## TYPICAL USES

- Aircraft Hangars & Maintenance Floors
- Commercial Bakeries and Kitchens
- Laboratories and Research Floors
- School & Universities
- Automotive Show Room and Repair Areas
- Hospital and Health Care Facility Floors
- Manufacturing and Warehouse Floors
- Pharmaceutical Floors

## BENEFITS

- Complies with USDA, FDA, FSMA. See Crown Polymers Technical Bulletin: 3 Food and Beverage Compliance.
- Slip Resistance (ADA) See Crown Polymers Technical Bulletin: 4 Coefficient of Friction.
- LEED requirements. See Crown Polymers Technical Bulletin: 5 LEED information
- Cures to an inert finish. See Crown Polymers Technical Bulletin: 2 VOC Compliance

## COLORS



## LIMITATIONS

- Do not add additional solvents
- Do not add pigments
- Apply in thin coats
- Higher temps result in lower working time

## SHELF LIFE

1 Year from Date of Manufacture provided unopened

## STORAGE

Store in a dry environment at room temperature and out of direct sunlight.

## DISCLAIMER

All technical bulletins, installation guidelines, guidelines, recommendations, statements, specifications, and technical data contained herein are based on information and tests. The accuracy and completeness of such tests are not guaranteed and are not to be construed as a warranty, expressed or implied. It is the responsibility of the user to document information and tests to determine the intent of the product for ones' own use. The application, job conditions and user assume all risks and liability resulting from use of the product, We do not suggest or guarantee any hazards listed herein are the only ones, which may exist, Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use the product. Recommendations or statements, whether in written or verbal, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Crown Polymers makes no claim that these tests or any other tests accurately represent all environments. Not responsible for typographical errors.

## LIMITED WARRANTY

Crown Polymers warrants its products to be free of manufacturing defects and meets all Crown Polymers current published physical properties. Crown Polymers' sole responsibility shall be to replace the portion of any product proved to be defective. There are no other warranties by Crown Polymers of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Crown Polymers shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty expressed or implied. In addition, no warranty or guarantee pertaining to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by applicator will be issued. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of substrate or structural defects are also excluded from limited warranty.

## APPLICATION EQUIPMENT

Personal Protective Equipment  
Jiffy Mixing Paddle  
Drill  
18" x 1/4" Nap Shedless Roller Cover  
5-7 Mil Notched Squeegee  
4" Chip Brush  
Spike Shoes

## SURFACE DIAGNOSTICS

Concrete must be structurally sound and free of all contaminants and bond breakers. Test concrete compressive strength using a Schmidt or Rebound Hammer to ensure substrate has compressive strength of 3500 psi or higher. Perform a PH test using concrete PH test strips or meter to ensure substrate PH is between 9-12. Perform Moisture Test using either Calcium Chloride per ASTM F1869 or In-Situ Relative Humidity Probe per ASTM F2170 to ensure substrate has Moisture Vapor Emission Rate of 3 lbs or less and Relative Humidity of 80% or less. See CrownTech Bulletin 6: Moisture Mitigation Negative Side Moisture Barrier

If Moisture Vapor Emission Rate is above 3 lbs. but below 25 lbs. and relative humidity is above 80% but below 99% then apply 8303 Moisture Barrier Primer first at 16 mils with a coverage rate of 100 Ft<sup>2</sup>/ Gal.

## SURFACE PREPARATION

Use Mohs scratch test to determine concrete hardness for proper diamond bond selection. Concrete should be mechanically profiled and prepared to produce a Concrete Surface Profile (CSP) level between #2 & #4 per ICRI Guideline no. 310.2R. See CrownTech Bulletin 1: Concrete Surface Preparation. All perimeter areas of coating termination shall be masked for protection. Saw cut and key-in all termination points.

## SURFACE REPAIR

All depressions, divots and cracks should be profiled and free of dust and contaminants. Repair surface imperfections to reduce the ability to see the defect through the coating. Honor all dynamic (moving) joints, static joints may be filled, use dynamic joints as initiation and termination points during application process where needed.

## TEMPERATURE EVALUATION

Ambient and substrate temps should be above 50°F and a minimum of 5°F above Dew Point. Product temps should be between 70-80°F. Relative Humidity should not exceed 80%. See CrownTech Bulletin 7: Temperature & Relative Humidity

## REFER TO SAFETY DATA SHEETS (SDS) FOR SAFETY PRECAUTIONS.

SAFETY PRECAUTIONS MUST BE FOLLOWED  
DURING STORAGE, HANDLING AND USE.

## PERSONAL PROTECTIVE EQUIPMENT (PPE)

SHALL BE WORN AT ALL TIMES INCLUDING  
BUT NOT LIMITED TO LONG SLEEVE SHIRTS OR  
DISPOSABLE ARM SLEEVES, SAFETY GLASSES,  
DISPOSABLE NITRILE GLOVES, AND PROPERLY  
FITTED NIOSH RESPIRATORS

ALL SOURCES OF IGNITION SHOULD  
BE TURNED OFF AND ENVIRONMENT  
SHOULD HAVE PROPER AND ADEQUATE  
VENTILATION DURING APPLICATION AND  
CURING PROCESS

MIXING AREA SHOULD BE PLACED ON OR IN  
CLOSE PROXIMITY TO PROJECT. AREA SHOULD  
BE SECURELY COVERED WITH PLASTIC,  
CARDBOARD OR TARP. STAGE MATERIALS,  
TOOLS AND CLEANING SUPPLIES IN MIXING  
AREA PRIOR TO APPLICATION PROCESS.

## MIXING PROCEDURE

- 1** Shake respective container for 30 seconds to ensure components are fully suspended.
- 2** If adding Anti-Slip add at a rate of 1/2 lb / gal into a 5-gal bucket along with 8101 and mix for 2-3 minutes at low RPMs until components are thoroughly blended

## COVERAGE RATE

300 Ft<sup>2</sup> / Gal @ 5.3 mils

## WORKING TIME

60 Minutes @ 75°F

WARMER AMBIENT, PRODUCT AND SURFACE  
TEMPERATURES AS WELL AS HIGHER RELATIVE  
HUMIDITY WILL SHORTEN POTLIFE AND  
WORKING TIME.

## APPLICATION PROCEDURE

- 1** Cut-in edges using a 4" chip brush. Do not allow wet edges to stand more than 10 minutes ahead of application of main body of floor.
  - 2** Pour a band of mixed material across the surface roughly 6-8" wide. Use 5-7 mil notched squeegee to gauge material across surface
    - Maintain wet edge
    - Always pour next mixed batch onto wet edge
    - Do not apply heavier than recommended coverage rates
  - 3** Back roll the surface with 18" x 1/4" nap roller by walking into the wet material wearing spike shoes and roll the surface wall to wall with overlap perpendicular to your first pass
    - Do not overwork material
- ✓ Allow coating to dry 1/2 - 1 Hrs @ 75°F  
Do not force dry.  
Recoat: 1-2 Hours  
Light Traffic: 24 Hours  
Heavy Traffic: 48 Hours  
Equipment Traffic: 72 Hours

## SLIP RESISTANCE

Skid-Resistance – Field (in situ) Wet Dynamic Coefficient of Friction (DCOF), ANSI A326.3. See Crown Polymers Technical Bulletin: 4 Coefficient of Friction.

## CLEAN-UP

Clean-up mixing station, tools, and equipment as required. Use acetone, a VOC exempt solvent, for cleaning up. Observe all legal, and health, and safety precautions when handling or storing solvents and materials, particularly in confined spaces. Make sure the working areas are well ventilated at all times during placement and curing time.

## DISPOSAL

Dispose of empty packaging and other waste in accordance with federal, state, provinces and local regulations.

## MAINTENANCE

Inspect the installed floor by spot cleaning and spot repairing the damaged or cracked areas. To prolong life of the flooring system, a daily maintenance program is highly recommended to ensure the floor is safe for its intended purposes. See Crown Polymers Technical Bulletin: 8 Care and Maintenance.

## TECHNICAL SUPPORT

For questions, contact a Crown Polymers Representative. Additional Support Documents are available from Crown Polymers, including brochures, application guidelines, videos and more. Visit [Crownpolymers.com](http://Crownpolymers.com) or contact Crown for additional resources