

PHYSICAL PROPERTIES

VOC	<100 g/L
SOLIDS CONTENT	38.5%
VOLUMETRIC MIX RATIO	2A:1B
COVERAGE RATE	350 ft ² /gal 4.6 Mils
APPLICATION TEMP	50°- 90°F
POTLIFE 1 Gal mass @ 75°F	45 Mins
DRY TIME @ 75°F	2-6 Hours
RECOAT WINDOW	Indefinite
FULL CURE	24 Hours
PACKAGING	1.5 Gal Kit 15 Gal Kit

MECHANICAL PROPERTIES

GLOSS INDEX 60° ASTM D523	Gloss: 90-95 Satin: 40-70
PENCIL HARDNESS ASTM D3363	3H
ADHESION TO CONCRETE ASTM D7234	>300 p.s.i

CHEMICAL RESISTANCE

Refer to CrownTech Chemical Resistance Guideline Technical Bulletin No. 9

PRODUCT DESCRIPTION

8105 CrownSeal Acrylic Polyurethane Primer/Sealer is a low viscosity, two-component acrylic polyurethane designed as a primer for Polyurethanes, such as 8110 CrownSeal CRU and as a concrete sealer. It is a film-forming sealer that leaves the surface with a wet look. It is a non-yellowing UV stable sealer that is available in clear gloss and clear satin. It cures to an inert, tough, concrete sealer. The recoat window, different than all other polyurethanes, is limitless, just make sure the surface is clean and free of contaminants. It is ideal for use as an irregular surface sealer, such as cementitious knock-downs, where an acrylic sealer is unacceptable. For added durability, place a second sealer coat. Apply 8105 CrownSeal Clear between 300 to 350 sq. ft. or 8105 CrownSeal Clear Satin between 400 to 450 sq. ft. (Not intended for use as a primer for epoxy coating or cementitious overlays.) It is designed for use in Southern California and is in compliance with SCAQMD air quality standards for Industrial Use Only.

TYPICAL USES

- | | | | |
|---|--|--------------------------------------|-------------------------|
| • Aircraft Hangars & Maintenance Floors | • Commercial Bakeries and Kitchens | • Laboratories and Research Floors | • School & Universities |
| • Automotive Show Room and Repair Areas | • Hospital and Health Care Facility Floors | • Manufacturing and Warehouse Floors | • Pharmaceutical Floors |

BENEFITS

- Complies with USDA, FDA, Food Safety Modernization Act.
- Slip Resistance (ADA)
- LEED® requirements.
- VOC and EPA Compliant, and low odor during installation. Cures to an inert finish.
- Strong and Tough Floor
- Strong Chemical and Abrasion Resistance
- Designed for new floors and for resurfacing old floors

COLORS



Clear Gloss



Clear Satin

LIMITATIONS

- Do not add additional solvents
- Satin requires a prime coat first
- Prime with 8303 if MVT is above 3 Lbs
- Do not apply below 30% Relative Humidity

SHELF LIFE

1 Year from Date of Manufacture provided unopened

STORAGE

Store in a dry environment at room temperature and out of direct sunlight.

DISCLAIMER

All technical bulletins, installation guidelines, guidelines, recommendations, statements, specifications, and technical data contained herein are based on information and tests. The accuracy and completeness of such tests are not guaranteed and are not to be construed as a warranty, expressed or implied. It is the responsibility of the user to document information and tests to determine the intent of the product for ones' own use. The application, job conditions and user assume all risks and liability resulting from use of the product, We do not suggest or guarantee any hazards listed herein are the only ones, which may exist, Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use the product. Recommendations or statements, whether in written or verbal, other than those contained herein shall not be binding upon the manufacturer, unless in writing and signed by corporate officer of the manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Crown Polymers makes no claim that these tests or any other tests accurately represent all environments. Not responsible for typographical errors.

LIMITED WARRANTY

Crown Polymers warrants its products to be free of manufacturing defects and meets all Crown Polymers current published physical properties. Crown Polymers' sole responsibility shall be to replace the portion of any product proved to be defective. There are no other warranties by Crown Polymers of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Crown Polymers shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty expressed or implied. In addition, no warranty or guarantee pertaining to appearance, color, fading, chalking, staining, shrinkage, peeling, normal wear and tear or improper application by applicator will be issued. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and/or physical movement of substrate or structural defects are also excluded from limited warranty.

APPLICATION EQUIPMENT

Protective Clothing
Jiffy Mixing Paddle
Slow Speed Drill
18" x 1/4" Nap Roller Cover
5-7 Mil Notched Squeegee
4" Chip Brush
Spike Shoes

SURFACE DIAGNOSTICS

Concrete must be structurally sound and free of all contaminants and bond breakers. Test concrete compressive strength using a Schmidt or Rebound Hammer to ensure substrate has compressive strength of 3500 psi or higher. Perform a PH test using concrete PH test strips or meter to ensure substrate PH is between 9-12. Perform Moisture Test using either Calcium Chloride per ASTM F1869 or In-Situ Relative Humidity Probe per ASTM F2170 to ensure substrate has Moisture Vapor Emission Rate of 3 lbs or less and Relative Humidity of 80% or less. See CrownTech Bulletin 6: Moisture Mitigation Negative Side Moisture Barrier

SURFACE PREPARATION

Use Mohs scratch test to determine concrete hardness for proper diamond bond selection. Concrete should be mechanically profiled and prepared to produce a Concrete Surface Profile (CSP) level between #2 & #4 per ICRI Guideline no. 310.2R. See CrownTech Bulletin 1: Concrete Surface Preparation

SURFACE REPAIR

All depressions, divots and cracks should be profiled and free of dust and contaminants. Repair cracks to reduce the ability to see the defect through the coating.

TEMPERATURE EVALUATION

Ambient and substrate temps should be above 50°F and a minimum of 5°F above Dew Point. Product temps should be between 70-80°F. Relative Humidity should not exceed 80%. See CrownTech Bulletin 7: Temperature & Relative Humidity

MIXING

- 1** Pre-Mix A-Component in its respective container using Jiffy mixer and drill at slow speeds for 30 seconds to ensure components are fully suspended.
- 2** Pre-Mix B-Component in its respective container using clean Jiffy mixer and drill at slow speeds for 30 seconds or until thoroughly homogeneous.
- 3** Transfer A-component and B-component at a mix rate of 2A:1B by volume into a clean 5-gal bucket (if adding aluminum oxide add #220 up to 1/2lb/gal or #320 up to 3 lbs/ gal) and mix for 2-3 minutes being sure to scrape sides of the bucket with a stir stick ensuring both components are thoroughly blended

COVERAGE RATE

350 Ft² / Gal @ 4.6 Mils wet film
(over primed/smooth surfaces)

WORKING TIME

15-25 Minutes @ 75°F

Warmer ambient, product and surface temperatures and high humidity will shorten potlife and working time.

APPLICATION STEPS

- 1** Cut-in stem walls using a 4" chip brush. Do not work edges more than 10 minutes ahead of main body of the floor.

Urethane sets slower in mass, only pour amount of mixed material as needed from bucket
- 2** Pour a band of mixed material across the surface roughly 4-6" wide. Use 5-7 mil notched squeegee to gauge material across surface
- 3** Back roll the surface with 18" x 1/4" nap roller by walking into the wet material wearing spike shoes and roll the surface wall to wall with overlap perpendicular to your first pass
- ✓** Allow coating to dry.
Light Foot Traffic – 24 Hours
Vehicular – 48 Hours

SLIP RESISTANCE

Skid-Resistance – Field (in situ) Wet Dynamic Coefficient of Friction (DCOF), ANSI A326.3. See Crown Polymers Technical Bulletin: 4 Coefficient of Friction.

CLEAN-UP

Clean-up mixing station, tools, and equipment as required. Use acetone, a VOC exempt solvent, for cleaning up. Observe all legal, and health, and safety precautions when handling or storing solvents and materials, particularly in confined spaces. Make sure the working areas are well ventilated at all times during placement and curing time.

DISPOSAL

Dispose of empty packaging and other waste in accordance with federal, state, provinces and local regulations.

MAINTENANCE

Inspect the installed floor by spot cleaning and spot repairing the damaged or cracked areas. To prolong life of the flooring system, a daily maintenance program is highly recommended to ensure the floor is safe for its intended purposes. See Crown Polymers Technical Bulletin: 8 Care and Maintenance.

TECHNICAL SUPPORT

For questions, contact a Crown Polymers Representative. Additional Support Documents are available from Crown Polymers, including brochures, application guidelines, videos and more. Visit Crownpolymers.com or contact Crown for additional resources

**REVIEW SAFETY DATA SHEETS
FOR PRECAUTIONS**