

PHYSICAL PROPERTIES

SOLIDS CONTENT	100%
VOC CONTENT	0 g/L
VOLUMETRIC MIX RATIO	2A:1B
APPLICATION TEMP	50°- 90°F
POTLIFE 1 Gal mass @ 75°F	20 Minutes
GEL TIME 1 Gal mass @ 75°F	37 Minutes
DRY TIME @ 75°F	5-12 Hours
RECOAT WINDOW	12-24 Hours
FULL CURE	7 Days
PACKAGING/COVERAGE	3 Gal Kit 480 Ft ² 15 Gal Kit 2400 Ft ² 150 Gal Kit 24000 Ft ²

MECHANICAL PROPERTIES

TEAR STRENGTH ASTM D624	565 pli
TENSILE STRENGTH ASTM D638	3,500 p.s.i
ELONGATION ASTM D638	20%
ADHESION TO CONCRETE ASTM D7234	>400 p.s.i Concrete Failure
ABRASION RESISTANCE ASTM D4060	0.026 g
SHORE D HARDNESS ASTM D2240	70-75
WATER ABSORPTION ASTM D570	0.15%

PRODUCT DESCRIPTION

8371 TerraCrown® is a 100% solids two-component, epoxy primer for Crown's thin-set epoxy terrazzo. 8371 TerraCrown® is used with 8373 TerraCrown WB Moisture Vapor Treatment Primer to create Crown's TerraCrown® Moisture Mitigation Primer. It is VOC Compliant in all states and provinces in North America.

TYPICAL USES

- Airport, Bus, Train Terminals
- Retail Spaces & Mall Common Areas
- School & Universities
- High End Designer Floors
- Hotel Lobbies & Office
- Hospital and Health Care Facility Floors
- Pharmaceutical Floors

BENEFITS

- Complies with USDA, FDA, FSMA. See Crown Polymers Technical Bulletin: 3 Food and Beverage Compliance.
- LEED requirements. See Crown Polymers Technical Bulletin: 5 LEED information

COLORS



Clear

LIMITATIONS

- Higher temperatures will result in shortened working times and faster drying time.
- Fiberglass or Scrim cloth recommended for dimensional stability
- Use 8303 CrownShield™ Moisture Barrier when MVT exceeds 3 lbs. or 80% RH

SHELF LIFE

1 Year from Date of Manufacture provided unopened

STORAGE

Store in a dry environment at room temperature and out of direct sunlight.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any product limitations are the only ones which may exist. Neither Seller nor Manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the products. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the Manufacturer, unless in writing and signed by an authorized corporate officer of Manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Manufacturer makes no claim that these tests or any other tests accurately represent all environments. Manufacturer is not responsible for typographical errors.



Scan QR code for full Disclaimer and Limited Warranty information