

PHYSICAL PROPERTIES

SOLIDS CONTENT	38%
VOC CONTENT	<5 g/L
VOLUMETRIC MIX RATIO	2A:1B
APPLICATION TEMP	60°- 90°F
POTLIFE 1 Gal mass @ 75°F	60 Minutes
DRY TIME @ 75°F	4-6 Hours
RECOAT WINDOW	12-24 Hours
FULL CURE	7 Days
PACKAGING	3 Gal Kit 15 Gal Kit

MECHANICAL PROPERTIES

ADHESION TO CONCRETE ASTM D7234	>400 p.s.i Concrete Failure
WATER ABSORPTION ASTM D570	<0.1%

PRODUCT DESCRIPTION

8373 TerraCrown® is a low viscosity, water-based, moisture vapor treatment epoxy primer. It is designed to penetrate and bond to properly prepared concrete substrates that may have high levels of moisture. It is used in conjunction with 8371 TerraCrown® Primer for the TerraCrown® Moisture Mitigation system. It is VOC Compliant in all states and provinces in North America.

TYPICAL USES

- General purpose primer with excellent wetting capabilities
- Can be used over properly prepared concrete that has high levels of moisture
- Used as a pre-primer prior to placing 8371 TerraCrown® Primer for TerraCrown® Moisture Mitigation System

BENEFITS

- Complies with USDA, FDA, FSMA. See Crown Polymers Technical Bulletin: 3 Food and Beverage Compliance.
- LEED requirements. See Crown Polymers Technical Bulletin: 5 LEED information

COLORS



Clear

LIMITATIONS

- Higher temperatures will result in shortened working times and faster drying time.
- Do not thin
- Do not add pigment
- Do not use over a fully sealed surface

SHELF LIFE

1 Year from Date of Manufacture provided unopened

STORAGE

Store in a dry environment at room temperature and out of direct sunlight.

DISCLAIMER

All guidelines, recommendations, statements, and technical data contained herein are based on information and tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. It is the user's responsibility to satisfy himself, by his own information and test, to determine suitability of the product for his own intended use, application and job situation and user assumes all risk and liability resulting from his use of the product. We do not suggest or guarantee that any product limitations are the only ones which may exist. Neither Seller nor Manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of, or inability to use, the products. Recommendations or statements, whether in writing or oral, other than those contained herein shall not be binding upon the Manufacturer, unless in writing and signed by an authorized corporate officer of Manufacturer. Technical and application information is provided for the purpose of establishing a general profile of the material and proper application procedures. Test performance results were obtained in a controlled environment and Manufacturer makes no claim that these tests or any other tests accurately represent all environments. Manufacturer is not responsible for typographical errors.



Scan QR code for full Disclaimer and Limited Warranty information